

Technical Data Sheet

Grade	Aluminized Spun Bond	
Basis Weight	271 g/m ²	
Thickness	0.61 mm	
Air Permeability	790 m ³ /m ² /h @ 200 Pa	
Electric Resistance	8.58 Ω (DIN 54345)	
Efficiency	0.3 – 1.0μ	78.2 %

1.0 – 3.0μ	97.3 %
------------	--------

3.0 – 5.0μ	100 %
------------	-------

5.0 – 10.0μ	100 %
-------------	-------

Average	91.2 %
---------	--------

