

Technical Data Sheet

Grade Oleophobic Spun Bond

Weight: g/m ² (oz./sq. yd.) ± 10 g (0.295 oz./sq. yd.)	260 (7.66)	Available in White or Black	Thickness: mm (in.)
± 0.03 mm (0.0012 in.)	0.61 (.024)		
Density: g/cm ³	.43		
Tensile Strength: kg. / 5 cm. (lbs./in.)	MD 91 (102)	Strip Method	
	CD 57 (64)		
Tearing Strength: kg. (lbs.)	MD 10.3 (22.7)	Single Tongue Method	
	CD 10.8 (23.8)		
Flex Resistance (Cycles)	50,000+	MIT Shape Method (Maximum Load: 2 kgs.)	
Bursting Strength: kg./cm. ² (lbs./sq. in.)	27.3 (388)	Mullen Method	
Air Permeability: cc/cm ² /sec. @ 1 /2 " W.G. (CFM) ± 3.0 (6.0)	10 (20)	Frazier Method	
Collection Efficiency: %	0.3 - 0.5 µm	48	Dust: Atmosphere
	0.5 - 1.0 µm	52	Velocity: 3.0m/min. (9.85 ft./min.)
	1.0 - 2.0 µm	86	
	2.0 - 5.0 µm	99	
	Over 5.0 µm	100	
Pressure Drop: mm Aq (in.)	5.3 (.21)		
Pore Size: µm	Minimum	23.6	Bubble Point Method
	Peak	29.6	
	Maximum	54.0	
Maximum Continuous Operating Temperature °C (°F)	120 (250)		
Maximum Short Term Operating Temperature °C (°F)	145 (295)	Maximum time: 30 minutes	
Relative Moisture Regain %	0.4	At 20° C (68° F) & 65% relative moisture	
Shrinkage (Maximum %)	MD + 0.8	At 135° C (275° F) for 8 hours	
	CD - 0.1		

KRAEMER
Manufacturing
1-800-443-6443
www.KraemerMFG.COM

